


## Comment on Graphene Nanoflakes with Large Spin: Broken-Symmetry States

Oleg V. Yazyev, Wei L. Wang, Sheng Meng, and Efthimios Kaxiras

*Nano Lett.*, 2008, 8 (2), 766-766 • DOI: 10.1021/nl073364z

Downloaded from <http://pubs.acs.org> on November 23, 2008



### More About This Article

Additional resources and features associated with this article are available within the HTML version:

- Supporting Information
- Links to the 2 articles that cite this article, as of the time of this article download
- Access to high resolution figures
- Links to articles and content related to this article
- Copyright permission to reproduce figures and/or text from this article

[View the Full Text HTML](#)

# Comment on Graphene Nanoflakes with Large Spin: Broken-Symmetry States

Oleg V. Yazyev,<sup>†</sup> Wei L. Wang,<sup>‡</sup> Sheng Meng,<sup>‡</sup> and Efthimios Kaxiras<sup>\*‡</sup>


*Institute of Theoretical Physics and Institut Romand de Recherche Numérique en Physique des Matériaux (IRRMA), Ecole Polytechnique Fédérale de Lausanne (EPFL), CH-1015 Lausanne, Switzerland, and Department of Physics and School of Engineering and Applied Sciences, Harvard University, Cambridge, Massachusetts 02138*

Received December 21, 2007


In a recent Letter,<sup>1</sup> Wang, Meng, and Kaxiras (WMK) proposed a strategy for constructing graphene fragments (nanoflakes) with large electron spin magnetic moments originating from the topological frustration of  $\pi$ -bonds. The elementary building block of the proposed magnetic graphene nanoflakes is a triangular fragment with 3-fold symmetry and a net magnetic moment stemming from the unequal number of carbon atoms in the two sublattices of graphene. As an extension of this idea WMK also considered a 6-fold symmetric “Star of David” graphene nanoflake, Figure 1a, and fractals structures derived from it. The magnetic moments of the proposed structures were verified by first-principles electronic structure calculations.

In the present paper, we point out that a more thorough analysis of spin states reveals the existence of broken-symmetry configurations<sup>2</sup> with antiferromagnetic (AF) correlation of locally spin-polarized regions. Calculations of such AF states are not always trivial and require explicit spatial spin-symmetry breaking for the initial guess wavefunctions. Additional first-principles calculations using such a broken spin-symmetry initial wavefunction show that the AF configuration of the Star of David with zero net spin, Figure 1b, is more stable (by 0.087 eV) than the originally considered high-spin state. This result is in full agreement with the Lieb theorem,<sup>3</sup> which predicts zero total spin for graphene nanoflakes with equal number of atoms in the two sublattices. Similar conclusions have been drawn for hexagonal graphene fragments<sup>4</sup> of the same symmetry. The  $S = 0$  configuration of this nanoflake naturally fulfills the preferred AF coupling between nearest neighbor atoms,<sup>5,6</sup> which is also true for fractal structures derived from it.

Here, we propose a modified strategy for generating fractal structures with large spin based on a building block consisting of a spin-polarized triangular fragment, the same as in the WMK proposal. Figure 2a shows such a fragment with total spin  $S_0 = (N_A - N_B)/2$  with  $N_A, N_B$  the numbers of atoms in sublattices A and B. Larger structures can be generated according to the Sierpinski sieve construction (fractal dimension  $d = \log_2 3 \approx 1.58$ ) as shown in Figure 2b,c for fractal levels  $q = 2$  and 4. In this case, no switch of



**Figure 1.** Two spin configurations of the “Star of David” structure: (a)  $S = 3$ ; (b)  $S = 0$ , antiferromagnetic, broken-symmetry ground state. Positive (blue) and negative (red) spin density isosurfaces are shown and regions with dominating A and B sublattice sites are marked.



**Figure 2.** Sierpinski sieve fractal structures of graphene nanoflakes with corresponding total spin  $S$ : (a) elementary triangular building block; (b)  $q = 2$  and (c)  $q = 4$  fractal structures. The two sublattice sites are shown as open and filled circles; the sublattice A sites dominate globally.

the sublattice where the majority spin resides is required, the number of atoms in sublattice A dominates globally for all fractal structures and as a result the large spin state is favored. The total spin increases with the fractal level  $q$  as  $S_q = S_0 3^q$  in accordance with the arguments presented by WMK. The results of our first-principles electronic structure calculations for  $q = 1, 2$  are in full agreement with the predicted total spins of the ground state configurations.

## References

- (1) Wang, W. L.; Meng, S.; Kaxiras, E. *Nano Lett.* **2008**, *8*, 241.
- (2) Noodleman, L. *J. Chem. Phys.* **1981**, *74*, 5737.
- (3) (a) Lieb, E. H. *Phys. Rev. Lett.* **1989**, *62*, 1201. (b) *Phys. Rev. Lett.* **1989**, *62*, 1927(E).
- (4) Fernández-Rossier, J.; and Palacios, J. J. *Phys. Rev. Lett.* **2007**, *99*, 177204.
- (5) Son, Y.-W.; Cohen, M. L.; Louie, S. G. *Phys. Rev. Lett.* **2006**, *97*, 216803.
- (6) Yazyev, O. V.; and Helm, L. *Phys. Rev. B* **2007**, *75*, 125408.

NL073364Z

\* To whom correspondence should be addressed.

<sup>†</sup> Ecole Polytechnique Fédérale de Lausanne (EPFL).

<sup>‡</sup> Harvard University.